


Wecryl 242 Mortar

Repair and levelling mortar



Material

Brief description

Wecryl 242 Mortar is a fast-reactive repair and levelling mortar used for filling and smoothing over faults and cavities in the substrate. Its properties also make it ideal for use on roads.

2-component, fast-reactive, highly filled PMMA-based (polymethyl methacrylate) repair and levelling mortar with a formulated filler mix

Properties and advantages

- Easy to apply
- Can also be applied at sub-zero temperatures
- Fast-curing
- Thermoplastic behaviour
- Stable under pressure
- Abrasion-resistant
- Watertight (subject to correct intermediate compression)
- Resistant to frost and de-icing salt
- Largely resistant to acids, alkali solutions and diesel
- UV-, hydrolysis- and alkali-resistant
- Solvent-free

Areas of application

Wecryl 242 Mortar is used as a repair and levelling mortar as well as to even out gradients on cement-bound and bitumen-bound substrates. Consequently it can be used as a reprofiling mortar under WestWood products, as a replacement for mastic asphalt or asphalt concrete, as a base mortar for installing manhole frames, for pressure distribution when the surfacing material is compressed or for forming lane grooves and for use as fixing mortar.

Packaging



1.00 kg	Wecryl 227 (resin)
9.00 kg	Wecryl 215 (filler mix)
<u>0.10 kg</u>	Catalyst (summer and winter)
10.10 kg	

3.34 kg	Wecryl 227 (resin)
30.00 kg	Wecryl 215 (filler mix)
<u>0.20 kg</u>	Catalyst (summer and winter)
33.54 kg	

Colours

Wecryl 242 Mortar is asphalt black.


Storage

Store products sealed in their original packaging and in a cool, dry and frost-free place. Avoid warm storage areas (> 30 °C) even for brief periods, for example on site. Consequently, the products must not be exposed to direct sunlight or kept in a vehicle. Unopened products have a shelf life of at least 3 months. After removing some of the contents, reseal the containers so they are airtight.

Wecryl 242 Mortar

Repair and levelling mortar

Application conditions



Temperatures

The product can be applied within the following temperature ranges:

Product	Temperature range, in °C		
	Air	Substrate*	Material
Wecryl 242 Mortar	-5 to +35	+3 to +50*	+3 to +30

* The substrate temperature must be at least 3 °C above the dew point during application and curing.

Moisture

The relative humidity must be $\leq 90\%$.

The surface to be coated must be dry and ice-free.

The surface must be protected from moisture until the coating has hardened.

Reaction times

	Reaction times for Wecryl 242 Mortar (at 20 °C)
Pot life	approx. 12 minutes
Rain-proof after	approx. 30 minutes
Can be walked on / overcoated after	approx. 1 hour
Curing time	approx. 3 hours

Higher temperatures will reduce reaction times, while lower temperatures will increase reaction times.

Consumption rates

2.2 kg/m² per mm layer thickness

Technical data

Density:

Wecryl 242 Mortar	2.19 g/cm ³
(Wecryl 227 (resin))	0.99 g/cm ³
(Wecryl 215 (filler mix))	2.61 g/cm ³

Product application



Application equipment / tools

For mixing the product:

- Stirrer with spiral mixer head

For applying the product:

- Smoothing trowel

Substrate preparation

The mortar is applied to the hardened WestWood Primer.

Mixing

Shake the resin component and add all of it to the sand mixture. Add the correct amount of catalyst for the container size (100 g for a 10 kg container, 200 g for a 33.34 kg container), then stir fully for 3 minutes using a compulsory mixer (spiral mixer head). There must be no lumps or nodules and all the material on the base and walls of the container must be



Wecryl 242 Mortar

Repair and levelling mortar

incorporated. To ensure that this is done, it is helpful to replot the material once during the mixing process.

Application

Pour the mortar onto the primed surface, compress and finish immediately with a smoothing trowel. The mortar can be applied in layer thicknesses of up to 50 mm in a single operation.

Please note: Make sure that the mortar is worked well into the corners (compressed).

Preparation for subsequent layers:

None required

Cleaning

If work is interrupted or when it is completed, clean the tools thoroughly with Weplus Cleaning Agent within the pot life of the material (approx. 10 minutes). This can be done with a brush. Do not use the tools again until the Cleaning Agent has evaporated fully.

Simply immersing the tools in the Cleaning Agent will not prevent the material from hardening.

Information on safety and risks

Please refer to the safety data sheets for the products used.

General information

The above information, especially information about application of the products, is based on extensive development work as well as many years of experience and is provided to the best of our knowledge. However, the wide variety of requirements and conditions on site mean that it is necessary for the product to be tested to ensure that it is suitable for the intended purpose. Only the most recent version of the document is valid. We reserve the right to make changes to reflect advances in technology or improvements to our products.

Rev: 24.07.2014