



Product information sheet

WeTraffic 493 Textured Surfacing High Performance



Brief description

WeTraffic 493 is a highly abrasion-resistant and extremely skid-resistant PMMA-based coating (PMMA = polymethyl methacrylate) that was developed specifically for use on roads and traffic zones with increased safety requirements. The optimum surface texture is achieved due to the outstanding properties of the particles already incorporated as a guide to layer thickness, and this helps to shorten braking distances considerably.

Material

2-component, rapid-curing, flexibilised, pigmented coating based on polymethyl methacrylate (PMMA) filled with bauxite (1 - 3 mm)

Properties

- Maximum abrasion-resistance, PSV of aggregate 70 - 80
- Superior skid resistance & grip > SRT 65
- Resistant to mechanical stress
- Chloride-resistant
- Easy and fast application
- Fast-curing
- Solvent-free

Areas of application

WeTraffic 493 increases road safety and is used on surfaces with braking and acceleration distances, on motorways, on transport routes such as crossings, tight bends, roundabouts or steep slopes.

Pack size



Summer:		Winter:	
15.00 kg	WeTraffic 493	15.00 kg	WeTraffic 493
<u>0.30 kg</u>	Wekat 900	<u>0.50 kg</u>	Wekat 900
<u>15.30 kg</u>		<u>15.50 kg</u>	

Colours

WeTraffic 493 is available in a range of colours, e.g.:

- RAL 7030 Stone grey
- RAL 7032 Pebble grey
- RAL 7043 Traffic grey
- Other colours are available on request.

Storage

Store products sealed in their original airtight container and in a cool, dry and frost-free place. The unopened product has a shelf life of at least 6 months after delivery. Direct sunlight on the containers should be avoided, including on site. After removing some of the contents, reseal the containers so they are airtight.



Product information sheet

WeTraffic 493 Textured Surfacing High Performance

Application conditions



Temperatures

The product can be applied within the following temperature ranges:

Product	Temperature range, in °C		
	Air	Substrate*	Material
WeTraffic 493	-10 to +35	-5 to +40*	+3 to +30

* The substrate temperature must be at least 3 °C above the dew point during application and curing.

Moisture

The relative humidity must be ≤ 90%.

The surface to be coated must be dry and ice-free.

The surface must be protected from moisture until the coating has hardened.

Reaction times and required amounts of catalyst

	WeTraffic 493 (at 20 °C)
Pot life	approx. 12 min
Rainproof	approx. 30 min
Can be walked on/ overcoated	approx. 45 min
Curing time	approx. 2 hours

Higher temperatures or greater proportions of catalyst will shorten reaction times, while lower temperatures and smaller proportions of catalyst will extend reaction times.

The following table indicates the recommended amount of catalyst required to adjust the curing reaction to the temperature.

Product	Substrate temperature in °C; required amounts of Wekat 900 in % w/w (guide)								
	-5	+3	+5	+10	+15	+20	+25	+30	+35
WeTraffic 493	3%	3%	2%	2%	1.5%	1.5%	1.5%	1%	1%

Consumption rates

Substrate

Asphalt / Concrete

Consumption


approx. 5.0 - 6.0 kg/m²

Technical data

Density:

approx. 1.85 g/cm³

Product application



Application equipment / tools

For mixing the product:

- Mixing tool with twin-paddle stirrer

For applying the product:

- Smoothing trowel

Surface treatment with:

- Textured roller



Product information sheet

WeTraffic 493 Textured Surfacing High Performance

Substrate preparation

The substrate must be suitably prepared so that it is sound, dry and free from loose or adhesion-reducing components.

Concrete:

Wecryl 176 is used as a primer on absorbent substrates, e.g. concrete. For further information please refer to the technical information sheet.

Asphalt:

We advise against applying the product to fresh asphalt less than 90 days old. No primer is required if the product is applied to asphalt older than 90 days.



Mixing

First stir the tub contents thoroughly.

Then add the catalyst while stirring at the slow-speed setting and mix for at least 2 minutes. Make sure that the product on the base and sides of the container is mixed in. Ideally WeTraffic 493 Textured Surfacing High Performance should be re-potted once and then stirred thoroughly again.

At product temperatures < 10 °C the product should be stirred for at least 4 minutes, as the catalyst will take longer to dissolve.

Application

Use a smoothing trowel or rubber squeegee to spread the material evenly and smooth it over, using the particle size as a guide to layer thickness. For an even surface (SRT>65) the area must be finished with a texturing roller immediately after application.

Cleaning

If work is interrupted or when it is completed, clean the tools thoroughly with WestWood Cleaning Agent within the pot life of the material (approx. 12 minutes). This can be done with a brush. Do not use the tools again until the Cleaning Agent has evaporated fully.

Simply immersing the tools in the Cleaning Agent will not prevent the material from hardening.

Information on safety and risks

Please refer to the safety data sheets for the products used.

General information

The above information, especially information about application of the products, is based on extensive development work as well as many years of experience and is provided to the best of our knowledge.

However, the wide variety of requirements and conditions on site mean that it is necessary for the product to be tested to ensure that it is suitable for the intended purpose. Only the most recent version of the document is valid. We reserve the right to make changes to reflect advances in technology or improvements to our products.

Rev.: 01 February 2022