


Product information

WPP 147

Primer for Polystyrene



Brief description

WPP 147 is a primer designed to act as a bonding agent between polystyrene substrates and WestWood waterproofing systems. WPP 147 is a high-grade, neutral, 1-component, permanently flexible, hybrid-polymerbased primer.

Material

1-component hybrid primer

Properties and advantages

- Easy to apply
- Permanently flexible when cured
- Smooths out irregularities and equalises tension in the material
- Grindable when cured
- Water-free
- Free from solvents, isocyanates, phthalates and silicone
- Non-corrosive
- Bubble-free curing even at high temperatures
- Colour-fast, weather-resistant and UV-resistant

Areas of application

WPP 147 is used to create a bond between polystyrene substrates and WestWood PMMA products.

Pack size

4.00 kg WPP 147



Colours white

Storage

Store products sealed in their original airtight container and in a cool, dry and frost-free place. Unopened, they have a shelf life of 12 months from the date of manufacture. Direct sunlight on the containers should be avoided, including on site. After removing some of the contents, reseal the containers so they are airtight.

Application conditions





Temperatures

The product can be applied within the following temperature ranges:

| Product | Temperature range, in °C | | | |
|---------|--------------------------|------------|-----------|---|
| | Air | Substrate* | Material | _ |
| WPP 147 | 0 to + 40 | 0 to +35* | +3 to +20 | |

^{*} The substrate temperature must be at least 3 °C above the dew point during application and curing.

WestWood Liquid Technologies Limited · 31 Morris Road · Nuffield Industrial Estate · Poole · Dorset · BH17 0GG · United Kingdom Tel.: +44 800 808 5480 · info@westwood-uk.com · www.westwood-uk.com Page 1 of 3



Product information

WPP 147

Primer for Polystyrene

Moisture

The relative humidity must be \leq 90%.

The surface to be coated must be dry and ice-free.

The surface must be protected from moisture until the coating has hardened.

Reaction times and required amounts of catalyst

| | WPP 147 | |
|-------------|------------------|--|
| | (at 23 °C) | |
| Overlayable | approx. 12 hours | |
| Curing time | approx. 24 hours | |

At lower temperatures, the curing process can take up to 48 hours.

Consumption rates Consumption

Smoothing trowel $0.7 - 0.9 \text{ kg/m}^2$

Technical data Density: 1.67 g/cm³

Shore hardness A: 40 ± 5

Product application

Application equipment / tools

For applying the product:

Smoothing trowel



Substrate preparation

The substrate must be clean and all dirt particles removed before WPP 147 is applied.

Application

The product is applied with a smoothing trowel



Preparation for subsequent layers

No preparation required

Cleaning If work is interrupted or when it is completed, clean the tools If work is

interrupted or when it is completed, clean the tools thoroughly with WestWood Cleaning Agent within the pot life of the material (approx. 20 minutes). This can be done with a brush. Do not use the tools again until the

Cleaning Agent has evaporated fully.

Simply immersing the tools in the Cleaning Agent will not prevent the

material from hardening.

Information on safety and risks Please refer to the safety data sheets for the products used.



Product information

WPP 147 Primer for Polystyrene

General information

The above information, especially information about application of the products, is based on extensive development work as well as many years of experience and is provided to the best of our knowledge. However, the wide variety of requirements and conditions on site mean that it is necessary for the product to be tested to ensure that it is suitable for the intended purpose. Only the most recent version of the document is valid. We reserve the right to make changes to reflect advances in technology or improvements to our products.

Rev.: 01 February 2022