


Wecryl 112

Primer for asphalt substrates



Brief description

Wecryl 112 is a fast-reactive primer used as a barrier on asphalt substrates in preparation for the later application of WestWood waterproofing or surfacing products.

Material

2-component, fast-reactive and flexibilised PMMA-based (polymethyl methacrylate) resin primer

Properties and advantages

- Very good adhesion to asphalt substrates
- Easy to apply
- Can also be applied at sub-zero temperatures
- Fast-curing
- Hydrolysis- and alkali-resistant
- Solvent-free

Areas of application

Wecryl 112 is used for the pre-treatment (primer and barrier coat) of asphalt substrates (e.g. mastic asphalt) ready for the later application of WestWood waterproofing or surfacing products.

Packaging



| | | | |
|----------------|--------------------------------|----------------|--------------------------------|
| Summer: | | Winter: | |
| 5.00 kg | Wecryl 112 | 5.00 kg | Wecryl 112 |
| <u>0.20 kg</u> | Wekat catalyst (2 x 0.1 kg) | <u>0.30 kg</u> | Wekat catalyst (3 x 0.1 kg) |
| 5.20 kg | | 5.30 kg | |
| Summer: | | Winter: | |
| 10.00 kg | Wecryl 112 | 10.00 kg | Wecryl 112 |
| <u>0.30 kg</u> | Wekat catalyst (3 x 0.1 kg) | <u>0.60 kg</u> | Wekat catalyst (6 x 0.1 kg) |
| 10.30 kg | | 10.60 kg | |

Colours

Wecryl 112 is available in the following standard colours:

- Clear (unpigmented, slightly yellowish)
- White


Storage

Store products sealed in their original airtight container and in a cool, dry and frost-free place. Unopened products have a shelf life of at least 6 months. Direct sunlight on the containers should be avoided, including on site. After removing some of the contents, reseal the containers so they are airtight.

Wecryl 112

Primer for asphalt substrates

Application conditions



Temperatures

The product can be applied within the following temperature ranges:

| Product | Temperature range, in °C | | |
|------------|--------------------------|------------|-----------|
| | Air | Substrate* | Material |
| Wecryl 112 | -5 to +35 | -5 to +50* | +3 to +30 |

* The substrate temperature must be at least 3 °C above the dew point during application and curing.

The substrate temperature must not be less than +3 °C if a topping is applied to the surface (see "Preparation for subsequent layers"). Reaction problems can occur at lower temperatures.

Moisture

The relative humidity must be ≤ 90 %.

The surface to be coated must be dry and ice-free.

The surface must be protected from moisture until the coating has hardened.

Reaction times and required amounts of catalyst

| | Wecryl 112 (at 20 °C, 3 % Wekat catalyst) |
|--|--|
| Pot life | approx. 15 minutes |
| Rain-proof after | approx. 30 minutes |
| Can be walked on / overcoated after | approx. 45 minutes |
| Curing time | approx. 3 hours |

Higher temperatures or greater proportions of Wekat catalyst will reduce reaction times, while lower temperatures and smaller proportions of Wekat catalyst will increase reaction times.

The following table indicates the recommended amount of Wekat catalyst required to adjust the curing reaction to the temperature.

| Product | Substrate temperature in °C / Required amounts of Wekat catalyst in % w/w (guide) | | | | | | | | | | | | | |
|---------|---|----|----|----|----|----|----|----|----|----|----|----|----|--|
| | -10 | -5 | +3 | 5 | 10 | 15 | 20 | 25 | 30 | 35 | 40 | 45 | 50 | |
| 112 | - | 6% | 6% | 6% | 4% | 4% | 2% | 2% | 2% | 2% | 1% | 1% | 1% | |

Consumption rates

| Substrate | Consumption |
|------------|------------------------|
| Smooth | 0.40 kg/m ² |
| Fine-sandy | 0.50 kg/m ² |
| Rough | 0.80 kg/m ² |

Technical data

| | |
|------------------|------------------------|
| Density (clear): | 1.03 g/cm ³ |
| Density (white): | 1,08 g/cm ² |

Wecryl 112

Primer for asphalt substrates

Product application



Application equipment / tools

For mixing the product:

- Twin-paddle stirrer

For applying the product:

- Sheepskin roller
- Brush (only for areas not accessible with roller)

Substrate preparation

The primer must only be applied to a prepared substrate. Please refer to the appropriate application guide for information about correct surface preparation.

Mixing

First stir the tub contents thoroughly.

Then add the Wekat catalyst while stirring the resin at the slow-speed setting and mix for 2 minutes. Make sure that the product on the base and sides of the container is mixed in.

At product temperatures < 10 °C the product should be stirred for 5 minutes, as the Wekat catalyst will take longer to dissolve.



Application

Use the sheepskin roller to apply an even film-forming coat of primer. Avoid creating puddles of primer.

Once the coating has cured, apply a second coat to cover any defects (bubbles, areas not fully coated).

Preparation for subsequent layers

For the subsequent application of Wecryl Mortar 242:

Once the primer has hardened, apply a second layer and top with a little quartz sand (0.1 – 0.2 kg/m² at 0.2 – 0.6 mm) while the primer is still wet. The sand topping creates the necessary key, i.e. roughness, for application of the mortar.

Never apply the topping to the first coat of primer.

Cleaning

If work is interrupted or when it is completed, clean the tools thoroughly with WestWood Cleaning Agent within the pot life of the material (approx. 10 minutes). This can be done with a brush. Do not use the tools again until the Cleaning Agent has evaporated fully.

Simply immersing the tools in the Cleaning Agent will not prevent the material from hardening.

Information on safety and risks

Please refer to the safety data sheets for the products used.

General information

The above information, especially information about application of the products, is based on extensive development work as well as many years of experience and is provided to the best of our knowledge. However, the wide variety of requirements and conditions on site mean that it is necessary for



Product information sheet

Wecryl 112 Primer for asphalt substrates

the product to be tested to ensure that it is suitable for the intended purpose. Only the most recent version of the document is valid. We reserve the right to make changes to reflect advances in technology or improvements to our products.

Rev: 01.02.2022